

RESIBLOCK INDIAN SANDSTONE SEALER **INVISIBLE**

APPLICATION GUIDE SUMMARY*

- 1 Make sure the surface and **jointing sand** are THOROUGHLY DRY and free from dirt.
- 2 Ensure that RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* is only applied when there is no risk of rain within the next 8 hours.
- 3 Do not apply in extremes of temperature (below 3° C or above 30° C). For temperatures above this range contact our application dept for special procedures.
- 4 Ensure paving is thoroughly swept and that where applicable no jointing sand remains in the chamfers of the pavers.
- 5 Apply to surface using a Resiblock application roller, remove any build up in depressions with a clean roller or builders sponge.
- 6 Application rates vary depending on porosity but will be in the order of 4-6m² per litre. Where the paving has a sand filled joint (nominal 5mm) material usage should be increased to 2-3m² per litre.
- 7 Avoid walking on the sealed area for 3 hours after application and do not drive motor vehicles on the surface for 24 hours.
- 8 ALWAYS WEAR PROTECTIVE GLOVES AND GOGGLES. NO SMOKING. WEAR A MASK WHEN WORKING IN CONFINED AREAS. Please refer to current MSDS.
- 9 All uncured sealant and tools should be cleaned immediately using RESICLEAN.

FOR FREE ADVICE TELEPHONE
RESIBLOCK
01268 273344

- * ***This fact sheet is not intended to replace the full application instructions, which must be read prior to application.***

Whilst Resiblock Limited believe that the data contained herein is factual, the opinions expressed are those of experts (qualified or otherwise) regarding the results of tests. The data is not to be taken as a warranty or representation for which Resiblock Limited assumes legal responsibility. This data is offered solely for your consideration, investigation and verification. Any use of this data must be determined by the user to be according to the applicable laws and regulations

Resiblock Limited try to ensure any advice, recommendations or information we may give in product literature is accurate and correct. However, we have no control over the circumstances in which our products are used, hence our advice does not release **end-users from the obligation to satisfy themselves by prior testing that the product/s is suitable for their specific application, and that the actual conditions of use are suitable.**

Accordingly no responsibility can be accepted, or any warranty given by ourselves, our representatives, agents or distributors. Each end-user should always ensure that they have consulted our latest publications and that the relevant information concerning this material is communicated to all members of their organisation handling our products.

Resiblock Limited's liability is for replacement of material proved to be defective only. Products are sold subject to our Standard Conditions of Sale.

The Company's policy of continuous product development and improvement renders specifications liable to modifications. Information provided in this literature is therefore subject to change without prior notification.

This entire document is copyright protected. All rights reserved. First published in Great Britain. No part of this publication may be produced, stored in a retrieval system, or transmitted in any form or by any means, electronic, mechanical, photocopying, recording and/or otherwise without prior written permission of the publishers.

© Resiblock Limited 1993