

RESIBLOCK INDIAN SANDSTONE SEALER INVISIBLE INSTALLATION INFORMATION

CONTAINER SIZES

RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* is available in 5 litre containers.

APPEARANCE

RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* in the container appears as a low viscosity clear liquid having a hydrocarbon odour. Application will not alter the appearance of the pavers upon full cure.

COVERAGE

RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* **IS NOT** a sand binder.

Application rates vary depending on porosity but will be in order of 4-6m² per litre. Where the paving has a sand filled joint avoid applying product to the joint. Coverage rates applicable for Indian Sandstone, Sandstone, Yorkstone & Limestone. For other types of natural stone please contact Resiblock's Technical Department (01268 273344).

SUBSTRATE/SURFACE CONDITIONS

The surface should be clean and free from oil, algae, dust and lime bloom. Surface temperature must be above 3°C and below 30°C. Application outside of these temperature ranges may be possible, but contact our technical department first for advice. Substrate must be dry; application to damp or wet surfaces can result in poor adhesion and discoloration. Allow 8 weeks between paver installation and sealing (see notes on efflorescence). Jointing sand which contains moisture can prevent bonding and stabilisation of joints. Do not use if rainfall is forecast within 8 hours of project completion.

Trade Tip. If you wish to see if the paving is perfectly dry, simply scrape out the jointing sand to a depth of 5-10mm; if it is dry, so is the paving.

If pavers/joints have been previously treated with any other stabiliser or sealer, please refer to our Technical Department prior to application.

PREPARATION - NEW WORK

On new work all that is usually required is a good sweep with a stiff broom, however if the surface has become partially weathered or contaminated, the area must be thoroughly pressure washed.

Application to poorly prepared paving particularly in respect of dampness can result in discoloration and disbonding.

PREPARATION - OLD WORK

This is probably the most essential part, in as much as it will determine the technical standard of the finished paved area. The pavers must be thoroughly cleaned using a pressure cleaner to remove all algae and lichen. This operation will also *blast out* all weeds and grass, and most of the top layer of jointing sand from between the blocks. It should also remove all food and drink stains along with any surface dirt and grime.

Note. Occasionally the action of washing or pressure washing will cause substrate saturation and/or reactivate efflorescence. Therefore allow 2 weeks between cleaning and application of RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* to allow to dry out and to check for lime-bloom reappearance.

SAND FILLED JOINTS ONLY

Once the substrate has been allowed to thoroughly dry, the joints between the pavers must be re-filled using kiln dried sand. This can be done simply by placing fine dried jointing sand onto the paving and sweeping in using a conventional soft broom. Finally completely remove surplus sand as previously described.

EQUIPMENT

RESIBLOCK *ROLLER OR BRUSH.*

METHOD OF APPLICATION

Apply to surface using a Resiblock application roller, remove any build up in depressions with a clean roller or builders sponge.

Note. Solvents are released during the cure that normally permeate through the sealer, however if the RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* is applied too thickly, the substrate is damp or excessively cold, bubbling may occur, giving the appearance of a white/milky residue.

TWO-COAT APPLICATION

A second coat is not normally recommended and may serve to darken paving. Please telephone +44 (0)1268 273344 for more information.

CURING PERIOD

Rapid initial cure will take place depending on ambient temperature, humidity and pver porosity; 3-6 hours can be expected. Immediately the surface is dry the paved area can be subjected to foot or light traffic but full chemical cure must be allowed to take place (24 hours) before being subjected to full traffic use.

STORAGE

Containers should be stored under cover and be protected from extremes of temperature. If stored at temperatures below 10°C, the polymer may tend to settle out of the solvent, as such ensure contents of container are thoroughly mixed.

Partly used kegs should not be stored. Any remaining traces of RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* in used drums must be cured by leaving the containers open; and in dry conditions, putting water into each container.

SHELF LIFE

RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE*, (unopened containers), has a shelf life of 18 months. All containers are marked with the use-by date

CLEANING TOOLS AND EQUIPMENT

RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* cures rapidly when exposed to atmospheric moisture, to give a film that can only be removed with great difficulty. For this reason it is recommended that all equipment be cleaned immediately using RESICLEAN. Do not use other solvents as unknown synergistic reactions may take place. Wash with water and detergent afterwards. RESICLEAN is also effective in the removal of splashes and spillages of uncured RESIBLOCK *INDIAN SANDSTONE INVISIBLE*.

EFFLORESCENCE

Efflorescence also known as 'lime bloom' or 'laitence', can affect the appearance of the paving surface, shown as *white powdery* patches before application of RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* or *creamish* patches after it has been applied. Clearly as it is almost impossible to remove our product, one should take steps to reduce the incidence of efflorescence before sealing with our material. Whilst lime bloom is a naturally occurring phenomenon, following these guidelines will considerably reduce the possibility of this nuisance spoiling your finished terrace or drive:-

1. Apply RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* after a dry spell of at least 48 hours. Ensure that the entire paved area is perfectly dry by checking the sand joints as described under "Substrate/Surface Conditions".
2. Allow 8 weeks *after installation of paing* before applying RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE*. The more serious cases of efflorescence should

appear during this period. On old installations allow at least 2 weeks after washing/pressure cleaning.

3. If lime bloom does show (before sealing), simply clean it off with RESIBLOCK *E.R.* (efflorescence remover). This will not only remove the white patches from the surface but from the upper layers of the blocks as well.
4. If in doubt please contact our technical department ***before*** using RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE*.

HEALTH AND SAFETY GUIDELINES

PVC gloves and protective clothing/face shield must be worn, plus use of a barrier cream on exposed areas of skin, as uncured RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* may be considered a hazardous material.

No smoking or naked flames, as RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* is **FLAMMABLE**. Ensure area to be treated is well ventilated. If public access is allowed, erect **NO SMOKING** signs and site fire extinguishers

A mask of the recommended type is **essential** when using a paintbrush, working close to the surface or internally. Sabre or Martindale is recommended.

Do not apply RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* in the presence of foodstuffs. Once fully cured RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* can be considered innocuous. Do not clean hands with RESICLEAN as solvents tend to de-fat skin that can lead to dermatological problems.

Do not return unused material to original containers. **DO NOT RESEAL** or store partly used kegs. Material so stored may have poor adhesion and Carbon Dioxide may generate and put the drum under pressure, which might rupture the drum. Furthermore partial or total solidification of the sealant may occur.

Please refer to Resiblock Limited's current Material Data Sheets for the latest and comprehensive information on this section.

LIMITATIONS

RESIBLOCK *INDIAN SANDSTONE SEALER INVISIBLE* is ***not suitable*** for pattern imprinted concrete, engineering bricks, quarry tiles, marble, exposed aggregate panels etc. Contact our technical department for more information.

*....and finally, we really do care! We at Resiblock Ltd are totally committed to ensuring you have the best possible job. So if you are in any doubt, **please telephone 01268 273344 before starting your project, for friendly professional advice.***

Whilst Resiblock Limited believe that the data contained herein is factual, the opinions expressed are those of experts (qualified or otherwise) regarding the results of tests. The data is not to be taken as a warranty or representation for which Resiblock Limited assumes legal responsibility. This data is offered solely for your consideration, investigation and verification. Any use of this data must be determined by the user to be according to the applicable laws and regulations.

Resiblock Limited try to ensure any advice, recommendations or information we may give in product literature is accurate and correct. However, we have no control over the circumstances in which our products are used, hence our advice does not release **end-users from the obligation to satisfy themselves by prior testing that the product/s is suitable for their specific application, and that the actual conditions of use are suitable.**

Accordingly no responsibility can be accepted, or any warranty given by ourselves, our representatives, agents or distributors. Each end-user should always ensure that they have consulted our latest publications and that the relevant information concerning this material is communicated to all members of their organisation handling our products.

Resiblock Limited's liability is for replacement of material proved to be defective only. Products are sold subject to our Standard Conditions of Sale.

The Company's policy of continuous product development and improvement renders specifications liable to modifications. Information provided in this literature is therefore subject to change without prior notification.

This entire document is copyright protected. All rights reserved. First published in Great Britain 1993. No part of this publication may be produced, stored in a retrieval system, or transmitted in any form or by any means, electronic, mechanical, photocopying, recording and/or otherwise without prior written permission of the publishers.

© Resiblock Limited 2009

S:\Resiblock ISS\INVISIBLE\Full application guidelines.doc