

# **RESIBLOCK RESIECCO**

## **APPLICATION GUIDELINES TO INSTALLED PAVING**

1. The pavers must be cleaned by using a pressure cleaner to remove all algae and lichen. This operation will also *blast out* any/all weeds and grass, and most of the top layer of jointing sand from between the blocks. It should also remove all food and drink stains along with any surface dirt and grime.
2. Once the substrate has been allowed to THOROUGHLY DRY/DRAIN (*please refer to Resiblock Technical Department if you are unsure of drying times or for further advice on cleaning/drying process*), the joints between the pavers must be re-filled using Kiln Dried Sand. This can be done simply by placing fine Kiln Dried Jointing Sand on the drive and sweeping into the joints using a conventional soft broom, ideally on the same day that the area is to be sealed with **RESIBLOCK RESIECCO**.
3. Ensure that the paving is thoroughly swept removing all surplus Kiln Dried Sand from the surface of the pavers and ensure that no jointing sand remains in the chamfers of the pavers. On non-chamfered paving sand must be swept at least 3-5mm from the surface.
4. Make sure the **paver surface** and **jointing sand** are **THOROUGHLY DRY** and free from dirt. Paving containing dampness will significantly reduce joint penetration and will prevent **RESIBLOCK RESIECCO** from mechanically bonding to the surface of the pavers.
5. Ensure that **RESIBLOCK RESIECCO** is only applied when there is no risk of rain within the next 24 hours.
6. Do not apply in extremes of temperature (below 5°C and above 30°C).
7. **Stir contents well.**
8. Apply to surface using a watering can (with a fine rose attached) and a **RESIBLOCK SQUEEGEE** drawing the sealer across the surface of the blocks and into the sand filled joints. Leave to sit on surface for 2-3 minutes before squeegeeing off. If applying to a riven surface, ensure **RESIBLOCK RESIECCO** is removed from dips/depressions with a clean rag/sponge to prevent pooling.
9. Accurate application rates are critical to ensure full joint stabilisation (typically 1 litre/2m<sup>2</sup> for standard Concrete Block Paving 100mm x 200mm).
10. **RESIBLOCK RESIECCO** is usually only applied as a 1 coat system.
11. Avoid walking on the sealed area until surface is dry and do not drive motor vehicles on the surface until joints have hardened.
12. ALWAYS WEAR PROTECTIVE GLOVES AND GOGGLES. Please refer to current MSDS.
13. All uncured sealant and tools should be cleaned immediately using water and detergent.

**RESIBLOCK RESIECCO** cannot be used on any previously sealed surfaces.  
For further advice on previously sealed surfaces contact RESIBLOCK's Technical Dept.

**FOR FURTHER FREE ADVICE TELEPHONE  
RESIBLOCK  
01268 273344**

*Whilst Resiblock Limited believe that the data contained herein is factual, the opinions expressed are those of experts (qualified or otherwise) regarding the results of tests. The data is not to be taken as a warranty or representation for which Resiblock Limited assumes legal responsibility. This data is offered solely for your consideration, investigation and verification. Any use of this data must be determined by the user to be according to the applicable laws and regulations*

*Resiblock Limited try to ensure any advice, recommendations or information we may give in product literature is accurate and correct. However, we have no control over the circumstances in which our products are used, hence our advice does not release **end-users from the obligation to satisfy themselves by prior testing that the product/s is suitable for their specific application, and that the actual conditions of use are suitable.***

*Accordingly no responsibility can be accepted, or any warranty given by ourselves, our representatives, agents or distributors. Each end-user should always ensure that they have consulted our latest publications and that the relevant information concerning this material is communicated to all members of their organisation handling our products.*

*Resiblock Limited's liability is for replacement of material proved to be defective only. Products are sold subject to our Standard Conditions of Sale.*

*The Company's policy of continuous product development and improvement renders specifications liable to modifications. Information provided in this literature is therefore subject to change without prior notification.*

*This entire document is copyright protected. All rights reserved. First published in Great Britain. No part of this publication may be produced, stored in a retrieval system, or transmitted in any form or by any means, electronic, mechanical, photocopying, recording and/or otherwise without prior written permission of the publishers.*

*© Resiblock Limited 1993*