

## **RESIBLOCK RESIFIX COMMERCIAL**

### **APPLICATION GUIDE SUMMARY\***

1. Make sure the surface is dry and free from detritus.
2. Ensure that RESIBLOCK RESIFIX *COMMERCIAL* is only applied when there is no risk of rain prior to compaction.
3. Do not apply if it is expected that temperatures will fall below 5°C.
4. Spread RESIBLOCK RESIFIX *COMMERCIAL* over paved surface evenly. Using a Resiblock Sand Squeegee sweep RESIBLOCK RESIFIX *COMMERCIAL* into joints with a slight pounding motion. Once a substantial area of pavement has been swept, use a rubber-soled plate compactor over the pavers in overlapping passes. Brush more RESIBLOCK RESIFIX *COMMERCIAL* into joints and compact same area again. Continue procedure until all joints are full and RESIBLOCK RESIFIX *COMMERCIAL* can no longer be vibrated into them.
5. Coverage is identical to conventional kiln dried jointing sand.
6. Carefully remove all excess RESIBLOCK RESIFIX *COMMERCIAL* from the face of the pavers, and to the bottom of the chamfers. Excess RESIBLOCK RESIFIX *COMMERCIAL* left on the surface will be difficult to remove.
7. Remove final traces of RESIBLOCK RESIFIX *COMMERCIAL* **and** activate the system by flooding with a hosepipe set to 'spray'. DO NOT use a pressure washer, ensure joints are saturated. Repeat process if necessary where water has not been fully absorbed into all joints.
8. A RESIBLOCK RESIFIX *COMMERCIAL* pavement is safe to walk on immediately, but ideally should be left to dry.
9. Ideally RESIBLOCK RESIFIX *COMMERCIAL* should not be subjected to cleaning regimes for 28 days.
10. Wear dust masks and normal PPE when using RESIBLOCK RESIFIX *COMMERCIAL*. Protect ornamental ponds/pools from wind blown dust.
11. RESIBLOCK RESIFIX *COMMERCIAL* can be washed off of skin with soap and warm water.

**FOR FREE ADVICE TELEPHONE  
RESIBLOCK  
01268 273344**

- \* ***This fact sheet is not intended to replace the full application instructions, which must be read prior to application.***

Whilst Resiblock Limited believe that the data contained herein is factual, the opinions expressed are those of experts (qualified or otherwise) regarding the results of tests. The data is not to be taken as a warranty or representation for which Resiblock Limited assumes legal responsibility. This data is offered solely for your consideration, investigation and verification. Any use of this data must be determined by the user to be according to the applicable laws and regulations

Resiblock Limited try to ensure any advice, recommendations or information we may give in product literature is accurate and correct. However, we have no control over the circumstances in which our products are used, hence our advice does not release **end-users from the obligation to satisfy themselves by prior testing that the product/s is suitable for their specific application, and that the actual conditions of use are suitable.**

Accordingly no responsibility can be accepted, or any warranty given by ourselves, our representatives, agents or distributors. Each end-user should always ensure that they have consulted our latest publications and that the relevant information concerning this material is communicated to all members of their organisation handling our products.

Resiblock Limited's liability is for replacement of material proved to be defective only. Products are sold subject to our Standard Conditions of Sale.

The Company's policy of continuous product development and improvement renders specifications liable to modifications. Information provided in this literature is therefore subject to change without prior notification.

This entire document is copyright protected. All rights reserved. First published in Great Britain 1993. No part of this publication may be produced, stored in a retrieval system, or transmitted in any form or by any means, electronic, mechanical, photocopying, recording and/or otherwise without prior written permission of the publishers.

© Resiblock Limited 1993