

RESIBLOCK RESINBOUND REFRESH is an exceptional rejuvenator and enhancer, environmentally friendly hard-wearing bonding sealer suitable for use with both Resin Bound and Resin Bonded surfaces/pavements. RESIBLOCK RESINBOUND REFRESH water-based PU/Acrylic hybrid dispersion formula will enhance the natural aggregate and rejuvenate original aesthetics.

1. Make sure the surface is clean, THOROUGHLY DRY and free from dirt and debris.
2. Ensure that RESIBLOCK RESINBOUND REFRESH is only applied when there is no risk of rain within the next 12 hours.
3. Do not apply in extremes of temperatures (below 5°C and above 30°C).
4. RESIBLOCK RESINBOUND REFRESH dries clear and is not recommended for Non-UV resins.
5. Stir contents well before use.
6. RESIBLOCK RESINBOUND REFRESH should be applied at a spread rate of 4-6m²/per litre with a RESIBLOCK RESI-ROLLER medium pile roller. Ensure RESIBLOCK RESINBOUND REFRESH is removed from depressions with a clean rag/sponge to prevent pooling where necessary.
7. Application rate will vary depending on size of aggregates, however a typical rate of 5m²/l (aggregate 6mm) can be expected.
8. RESIBLOCK RESINBOUND REFRESH is usually only applied as a 1 coat system. A second coat can be applied if necessary, after two hours. Any second coat at half the spread rate of the first coat.
9. Avoid walking on the sealed area until surface is dry and do not drive motor vehicles on the surface until hardened. Minimum 24 hours.
10. ALWAYS WEAR PROTECTIVE GLOVES AND GOGGLES. Please refer to current SDS.
11. All uncured sealant and tools should be cleaned immediately using water and detergent.
12. It is recommended to trial on a small inconspicuous area so as to assess suitability. Product samples available via www.resiblock.com or 01268 273344